



**Summary of Substantive Changes
between the 2012 and the 2012a editions of
ASTM D2513, "Polyethylene (PE) Gas Pressure Pipe Tubing, and Fittings"**

Presented to the IAPMO Standards Review Committee on May 7, 2012

General: The changes to this standard should not require additional testing of currently listed products. The changes are:

- Revised Table 1

Table 1, Polyethylene Compound Requirements: The minimum HDB at 140°F (60 °C) for PE 2708 and PE 4710 was changed from ~~1000 psi (6.0 MPa)~~ to 800 psi (5.5 MPa).